

## Core **Toroid 102/66/15**



Effective parameters				
	Parameter	Value	Unit	
	$\Sigma(I/A)$	core factor (C1)	0.956	mm <sup>-1</sup>
	<b>Ve</b>	effective volume	68200	mm <sup>3</sup>
	<b>Le</b>	effective length	255	mm
	<b>Ae</b>	effective area	267	mm <sup>2</sup>
	<b>m</b>	mass of core	≈ 325	g/pcs

Epoxy coating DC isolation voltage 2000.

Maximum operating temperature of the coating is 200°C.

### Dimensions (mm)

Cores	OD	ID	H	
<b>T102/66/15</b>	102 ± 2	65.8 ± 1.3	15 ± 0.5	Uncoated
<b>TX102/66/15</b>	104.5 max	64.1 min	16 max	Epoxy Coated

### Core data

Cores	Material	AI (nH/turns <sup>2</sup> )	AI tolerance	μe
<b>T102/66/15</b>	3C11	5690	± 25%	≈ 4300
<b>T102/66/15</b>	3C94	3040	± 25%	≈ 2300
<b>T102/66/15</b>	3E27	7270	± 25%	≈ 5500

### Core data

Cores	Material	AI (nH/turns <sup>2</sup> )	AI tolerance	μe
<b>TX102/66/15</b>	3C11	5690	± 25%	≈ 4300
<b>TX102/66/15</b>	3C94	3040	± 25%	≈ 2300
<b>TX102/66/15</b>	3E27	7270	± 25%	≈ 5500